KOOLBLACK TECHNOLOGY

KOOLBLACK® Technology eliminates the tradeoffs between aesthetics and performance by incorporating near-infrared, heat reflective properties into dark color screen fabrics. This feature, coupled with the other benefits of dark colored fabrics, provides excellent contrast for a clear view through, uniformed exterior building design, maximized energy savings and optimized occupant comfort.


T Screen[™] with KOOLBLACK[®] Technology:

T Screen with KOOLBLACK" Technology is the best performing fabric in its category for surface heat reflectance. With this proprietary shade product, buildings can be utilized more efficiently through maximizing the area of working space and decreasing energy load.


- Woven with KOOLBLACK[®] Technology infused dark yarns and reflective white yarns for enhanced heat reflection
- KOOLBLACK[®] dark yarns provide unmatched surface heat reflectance for less interior radiated heat and more comfortable working spaces around the shade installation
- Reduces overall visible light transmittance (Tv) for superior views, glare control and the same daylighting benefits of conventional dark shade fabrics.
- High infrared reflectance, RS (IR), for reduced temperatures and cooling costs

DARK SIDE TO INTERIOR

WHITE SIDE TO EXTERIOR



REFLECTS RADIATION AND CONTROLS HEAT



CLEAR, CRISP OUTWARD VISIBILITY



More information on Mermet's full line of KOOLBLACK® Technology fabrics, E Screen with KOOLBLACK® Technology and T Screen[™] with KOOLBLACK[®] Technology, can be found at www.mermetusa.com.



Specifications

| Item Number | 1% 009701 3% 009703 5% 009705 |
|--------------------|---|
| Product Category | High Performance |
| Fabric Style | Satin |
| Openness Factor | 1%, 3% & 5% |
| Composition | 36% Fiberglass 64% Vinyl |
| UV Blockage | Approximately 95% - 99% |
| Standard Packaging | Rolls of 30 ly (27 lm) |
| Width | 98" (250 cm), 122" (310 cm) |
| Weight | 1% 13.54 oz/yd² (459g/m²)±5% 3% 13.27 oz/yd² (450 g/m²)±5% 5% 12.48 oz/yd² (423 g/m²)±5% |
| Thickness | 1% 0.024 in (0.61 mm) ±5% 3% 0.029 in (0.74 mm) ±5% 5% 0.027 in (0.69 mm) ±5% |
| | |
| | |

NFPA 701-10 TM#1, California U.S. Title 19

RoHS - Lead Free, GREENGUARD Gold

ASTM E2180, ASTM G21

CAN/ULC-S109-03 Small & Large Flame Test

Classifications

Fire Classifications

Bacterial & Fungal Resistance Environment Acoustical Performance

Fabrication

| | | WITH |
|---|---------|-----------|
| Т | Screen™ | KOOLBLACK |

Cutting: Cold, Ultrasonic or Crush | Welding: Radio Frequency, High Frequency, Impulse, Hot Air or Wedge We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabric specifications.

1% NRC: 0.10, SAA: 0.11 3% NRC: 0.15, SAA: 0.14 5% NRC: 0.10, SAA: 0.09

| T Screen™ KOOLBLACK | | | | FABRIC | | | | | | | | | | | | | | | F A B | RIC | + G L A S S | | | |
|---------------------|----------------------|------------|-----------|--------|----|-----------------------------------|----|----|----|--------|----|----|--------|----|---------|--------|----|---|-------|--------|-------------|----|-----------|----------------|
| | | | | | | ^{thermal} Total Solar | | | | | | | | | optical | | | | | | commercial | | | residential |
| | | | Rs IR % | | | Rs % | | | A | As % | | | Ts % | | | Rv % | | | | Tv % | | | % nent | SHGC |
| ITEM | COLOR | SIDE* | 1 | 3 | 5 | 1 | 3 | 5 | 1 | 3 | 5 | 1 | 3 | 5 | 1 | 3 | 5 | 1 | 3 | 5 | 1 | 3 | 5 | 135 |
| 002131 | White/Grey | Streetside | 72 | 70 | 67 | 69 | 68 | 63 | 18 | 18 | 20 | 13 | 14 | 17 | 69 | 68 | 60 | 7 | 9 | 11 | 55 | 53 | 47 | 0.28 0.29 0.33 |
| | | Roomside | 70 | 69 | 67 | 52 | 53 | 49 | 36 | 34 | 35 | 12 | 13 | 16 | 38 | 39 | 35 | 6 | 7 | 10 | 34 | 34 | 32 | 0.39 0.39 0.42 |
| 002032 | White/Cocoa | Streetside | 71 | 67 | 64 | 68 | 62 | 57 | 19 | 23 | 26 | 13 | 15 | 17 | 67 | 60 | 53 | 7 | 8 | 10 | 53 | 45 | 39 | 0.30 0.35 0.39 |
| | | Roomside | 69 | 65 | 63 | 46 | 44 | 41 | 41 | 40 | 41 | 13 | 16 | 18 | 26 | 27 | 22 | 6 | 9 | 10 | 26 | 24 | 21 | 0.45 0.47 0.50 |
| 002035 | White/Charcoal | Streetside | 69 | 66 | 64 | 65 | 62 | 57 | 24 | 23 | 26 | 11 | 15 | 17 | 63 | 60 | 52 | 4 | 8 | 9 | 50 | 45 | 39 | 0.31 0.35 0.39 |
| | | Roomside | 67 | 65 | 62 | 43 | 43 | 39 | 46 | 41 | 43 | 11 | 16 | 18 | 24 | 25 | 19 | 4 | 9 | 10 | 26 | 24 | 18 | 0.46 0.47 0.51 |
| 00K131 | White/Charcoal-Grey | Streetside | 72 | 69 | 66 | 69 | 66 | 61 | 20 | 20 | 22 | 11 | 14 | 17 | 68 | 66 | 58 | 4 | 7 | 10 | 55 | 53 | 45 | 0.28 0.30 0.34 |
| | | Roomside | 70 | 67 | 65 | 48 | 48 | 45 | 41 | 38 | 38 | 11 | 14 | 17 | 30 | 32 | 27 | 4 | 7 | 10 | 29 | 32 | 26 | 0.41 0.42 0.45 |
| 00K302 | White/Charcoal-Cocoa | Streetside | 69 | 67 | 64 | 65 | 62 | 57 | 22 | 23 | 26 | 13 | 15 | 17 | 64 | 60 | 53 | 7 | 8 | 9 | 50 | 45 | 39 | 0.32 0.35 0.39 |
| | | Roomside | 67 | 65 | 62 | 44 | 44 | 40 | 44 | 40 | 43 | 12 | 16 | 17 | 25 | 26 | 20 | 6 | 9 | 10 | 26 | 24 | 21 | 0.45 0.47 0.50 |

*Roomside: identified by the color side; Streetside: identified by the white side.

Warranty

Care & Handling

Mermet Corporation 5970 N. Main Street ■ Cowpens, SC 29330 Ph 1.866.902.9647 info@mermetusa.com

mermetusa.com

5 Year Exterior & 10 Year Interior

Remove dust with a vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or soft brush dipped in soapy water using a mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.


The fabric performance tests were conducted in accordance with ASTM F891 & ASTM F903-96: Total Solar Transmittance (Ts). Total Solar Reflectance (Rs), Solar Reflectance in Infrared (Rs IR), Total Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / ½° air / 6 mm with low E on surface #2. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For residential SHGC data and the most up-to-date test results, performance specifications, and larger samples, contact the Mermet Technical Department at: www.mermetusa.com.

T ScreenTM | **Koolblack** High Performance | 1% 3% 5% openness






Architects and designers no longer have to sacrifice occupant comfort, the aesthetic of the façade or building envelope performance when specifying shade solutions.



FABRIC | T SCREEN" WITH KOOLBLACK TECHNOLOGY COLOR | WHITE CHARCOAL VIEW | INSIDE



FABRIC | T SCREEN" WITH KOOLBLACK TECHNOLOGY COLOR | WHITE CHARCOAL VIEW | OUTSIDE